

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MX	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Morocco	UA	Ukraine
BR	Brazil	IL	Israel	MT	Malta	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KR	Korea	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

WO 98/54165

PCT/IL98/00245

## A PROCESS FOR THE EPOXIDATION OF ALKENES


### Technical Field

The present invention relates to the catalytic activation of molecular oxygen for alkene epoxidation using transition metal substituted polyoxometalates as catalysts.

### Background Art

Epoxidation of alkenes is an important chemical transformation whereby an oxygen atom is added to a carbon-carbon double bond to form an epoxide. Epoxides are often utilized as intermediate compounds which can then be transformed to final products. Examples include but are certainly not limited to ethylene glycol and polyethylene glycol from ethylene oxide, propylene glycol from propylene oxide, phenylacetaldehyde from styrene oxide and propranolol from 2R-glycidol.

Epoxidation of alkenes can be carried out using numerous techniques. The oldest and probably most common method is to react the alkene with an organic peracid, according to the reaction set forth in equation (1).



Typical peracids used in the art include perbenzoic acid, peracetic acid, performic acid, perphthalic acid and substituted perbenzoic acids such as 3-chloroperbenzoic acid. The salts of such acids may also be effective oxidants as in the case of magnesium monoperoxophthalate. The acids may be used as pure compounds or as prepared *in situ* in the reaction mixture by for example adding hydrogen peroxide to acetic anhydride to form peracetic acid. Although processes based on the reaction as described in equation (1) are known, there are certain drawbacks that are associated with such reactions. Among these one may cite (a)


WO 98/54165

PCT/IL98/00245

2

the propensity for formation of by-products such as glycols and glycol esters by reaction of the epoxide with water and/or acid in the reaction medium, (b) the necessity of recovering and/or recycling the acid co-product and (c) the necessity for stringent reaction control because of the safety danger involved in use of organic peracids (acyl hydroperoxides).

In order to minimize the danger in using peroxides as oxidants the use of alkyl and alkylaryl hydroperoxides in place of acyl hydroperoxides has been suggested and applied. These oxidants do not normally react with alkenes and the addition of a catalyst is required as shown in the reaction illustrated in equation (2).



Some hydroperoxides commonly used in such reactions are *tert*-butylhydroperoxide, cumene hydroperoxide and ethylbenzene hydroperoxide. The catalysts used are most commonly based on compounds containing Ti(IV), V(V), Mo(VI) or W(VI) although many compounds based on other metals have been described as being effective catalysts. These reactions are safer because of the lower reactivity of alkyl and alkylaryl hydroperoxides compared to organic peracids, however, the other disadvantages associated with the use of acyl hydroperoxides remain. Thus, reactions are not necessarily more selective, since the presence of catalysts often leads to additional side reactions, for example, substitution and oxidation at the allylic carbon of the alkene instead of oxygen addition to the double bond. Similar to the problems encountered with the use of acyl hydroperoxides, the alcohol co-product must be recovered, recycled and/or otherwise utilized.


A further method to epoxidize alkenes is to use aqueous hydrogen peroxide

WO 98/54165

PCT/IL98/00245


3

as oxidant as shown in the reaction illustrated in equation (3).



Such a reaction represents a conceptual improvement compared to the use of organic hydroperoxides in that the co-product is water and therefore is environmentally benign and need not be recovered or recycled. As in the use of alkyl- and alkylaryl hydroperoxides the presence of a catalyst is necessary, which catalysts are again often compounds containing Ti(IV), V(V), Mo(VI) or W(VI), among others. In only certain cases has high selectivity been reported for alkene epoxidation. Some effective and selective catalysts include titanium silicalite-1 and other titanium substituted zeolites, and polyoxometalates such as  $[\text{WZnMn}_2(\text{ZnW}_9\text{O}_{19})_2]^{12-}$  and  $\{\text{PO}_4[\text{WO}(\text{O}_2)_2]_4\}^{3-}$ . In many cases, the use of hydrogen peroxide represents an ideal oxidant provided reactions are selective. An exception is in cases where the low price of the epoxide make the use of hydrogen peroxide prohibitively expensive.

An additional important method for synthesis of epoxides from alkenes is via formation of a halohydrin, preferably a chlorohydrin, using hypochlorous acid in the first step, followed by use of base eg NaOH for ring closure in the second step, as shown in the reaction illustrated in equation (4).



This is a very simple procedure which has, however, two problems. First, usually the presence of molecular chlorine in hypochlorous acid leads to formation

WO 98/54165

PCT/IL98/00245

4

of dichlorinated organics which are undesirable by-products and must be disposed of. Second, the process also forms large amounts of salts as co-product which also must be treated or recycled.

The ideal oxidant for alkene epoxidation both from an ecological and economic point of view would be molecular oxygen (dioxygen) as found in air. The addition of dioxygen to an alkene is disfavored kinetically, thus catalytic procedures need to be applied. In cases where there is no allylic carbon to the double bond, oxygen may be added to the double bond using a silver catalyst at elevated temperatures. In this way, ethylene oxide is manufactured from ethylene. For similar procedures with other alkenes, such as 1-butene, propene etc. this reaction fails to give epoxide in significant amounts. The basic problem in use of dioxygen for epoxidation of alkene lies in the radical nature of the molecular oxygen molecule. In homogenous reactions, this radical nature always leads to a preferred radical reaction via substitution of hydrogen at an allylic carbon atom. Therefore, the common mode of utilization of dioxygen in liquid phase catalyzed reactions does not yield epoxide as a major product. The situation in gas phase reactions is similar wherein activation of alkenes leads to allylic type carbocations, carbanions or carbon radicals again preventing formation of epoxides as a significant product.

Conceptually, in order to use dioxygen for alkene epoxidation, activation of dioxygen should be via formation of a high valent metal oxo compound formed after scission of the oxygen-oxygen bond. These high valent metal-oxo intermediates are effective epoxidizing agents. Most commonly this is carried out in nature by use of monooxygenase type enzyme such as cytochrome P-450 or methane monooxygenase. Such enzymes may be mimicked, for example, by using manganese and iron porphyrins as catalysts. The monooxygenase mechanism, however, requires two electrons from a reducing agent in order to cleave the oxygen-oxygen bond leading to formation of the high valent metal-oxo intermediate active in alkene epoxidation. From a process point of view the reducing agent

WO 98/54165

PCT/IL98/00245

5

becomes the limiting reagent instead of dioxygen and negates the attractivity of such a process.

The alternative is activation of dioxygen in a dioxygenase type mechanism. In such a reaction, dioxygen is cleaved using two metal centers leading to formation of two high valent metal-oxo species. This type of reaction has been only realized using a ruthenium substituted tetramesitylporphyrin (RuTMP). Turnover rates to epoxide are very low and the catalyst has limited stability.

The limited stability of porphyrin ligands has led to the suggestion that transition metal substituted polyoxometalates may be important alternative catalysts to metalloporphyrins as disclosed and discussed in Hill, US Patent 4,864,041. These catalysts would retain the high activity of their metalloporphyrin counterparts, however, are significantly more thermally and oxidatively stable, thus allowing their use as long living catalysts. This previous work describes the application of transition metal substituted polyoxometalates for the epoxidation of alkenes using oxygen donors such as iodosylbenzene. Other reported academic research has evolved from this report and has described alkene epoxidation using other oxygen donors such as *tert*-butylhydroperoxide, hydrogen peroxide and *p*-cyano-*N,N*-dimethylaniline-*N*-oxide. The use of transition metal substituted polyoxometalates as catalysts for alkene epoxidation with molecular oxygen has never been described.

#### Disclosure of the Invention

Accordingly, it is an object of this invention to provide a novel process for the epoxidation of alkenes using molecular oxygen as oxidant. It is also an object of this invention to provide a method for carrying out this epoxidation of alkenes with molecular oxygen using a transition metal catalyst. Furthermore, it is an objective of this invention to carry out said epoxidation using a transition metal substituted polyoxometalate as catalyst.

PCT/IL98/00245


WO 98/54165

6

According to the present invention there has now been discovered a process which uses transition metal substituted polyoxometalates as catalysts for the epoxidation of alkenes with molecular oxygen.

More particularly the present invention provides a process for the catalytic epoxidation of alkene comprising contacting a transition metal substituted polyoxometalate and molecular oxygen with alkene.

The process described in this invention relates to the use of transition metal substituted polyoxometalates (TMSP) to catalyze the epoxidation of alkenes with molecular oxygen according to the following equation (5).



Polyoxometalates are oligomeric oxides of defined structure based on addenda of tungsten, molybdenum, niobium or vanadium or a combination thereof. More specifically, transition metal substituted polyoxometalates are compounds of the general formula  $X_x(\text{TM})_y\text{M}_m\text{O}_z^{q-}$  where the heteroatom, X, if present ( $x \geq 0$ ) may be main group or transition metals, the addenda atoms, M, are molybdenum, tungsten, niobium or vanadium or a combination thereof, and TM is one or several different transition metals. The specific class of transition metal substituted polyoxometalates,  $[\text{WZnTM}_2(\text{XW}_9\text{O}_{19})_2]^{q-}$ , used in the process described by the present invention are characterized as a dimer of a truncated Keggin structure having a "belt" of W, Zn and other transition metal (TM) cations "sandwiched" between the two  $\text{B-XW}_9\text{O}_{34}$  trivacant Keggin fragments the structure of which is shown in appended Figure 1. The transition metal cations are assumed to be positioned at terminal positions and are hexacoordinate with at least one labile ligand such as water. The TM atom can be any transition metal of the first, second or third row. More preferably the TM atom is a noble metal selected from the group

WO 98/34165

PCT/IL98/00245

7

consisting of ruthenium, rhodium, palladium, osmium, iridium and platinum. Most preferably the TM atom is ruthenium. The heteroatom atom, X, of the trivacant Keggin fragments can be any heteroatom known for Keggin compounds as is well-known in the art. For example, X can be a nonmetal such as phosphorous, silicon, germanium, boron, or arsenic. Alternatively X can be a metal such as zinc, cobalt, iron etc. The preferred transition metal substituted polyoxometalate for this process is  $[\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2]^{11-}$ . No transition metal substituted polyoxometalates or those of the general structure described and shown above have ever been used as catalysts for the epoxidation of alkenes with molecular oxygen. The counter cation of the above transition metal substituted polyoxometalates may be any cation including for example alkali metals, alkaline earth cations, transition metal cations or organic cations such as quaternary ammonium salts.

The catalytic reaction as described in equation (5) is carried out by contacting the catalyst with molecular oxygen and alkene. In one process the catalyst is contacted with molecular oxygen, followed by contact with the alkene. In another process the catalyst is contacted simultaneously with both the molecular oxygen and alkene. The reaction or contact between the catalyst and reactants (alkene and molecular oxygen) may take place in a solvent whereby the reactants are added to the catalyst dissolved in an liquid phase. Some typical solvents are aliphatic, aromatic or halogenated hydrocarbons. Some exemplary solvents of these classes are 1,2-dichloroethane, heptane, toluene, xylene, chlorobenzene or mixtures thereof. Alternatively, the catalyst may be placed on a support or used as a simple solid followed by addition of the reactants. The support used for the catalyst may be any support used in heterogeneous catalysis including among others silica, alumina and other oxides.

The alkenes applicable as reactants in this process may be any type of alkenes known. This includes simple terminal and linear alkenes such as ethene, propene, 1-butene, 1-octene etc. The alkene may be an internal branched or linear alkene such as 2-butene, 2-octene, 2-methyl-2-heptene, 2,3-dimethyl-2-butene, etc.



PCT/IL98/00245

WO 98/54165

8

The alkene may also be cyclic for example cyclohexene, cyclooctene, norbornene, etc. Molecular oxygen may be used pure, as air, as oxygen enriched air, or as oxygen depleted air. Inert gases may be added. The suggested temperature range of the reaction is between 0 and 350 °C. More preferably between 25 and 250 °C and most preferably between 60 and 180 °C. The reaction may be operated at atmospheric, sub-atmospheric or super-atmospheric pressures. Most preferably the reaction is run at super-atmospheric pressures.

While the invention will now be described in connection with certain preferred embodiments in the following examples and with reference to the accompanying figures so that aspects thereof may be more fully understood and appreciated, it is not intended to limit the invention to these particular embodiments. On the contrary, it is intended to cover all alternatives, modifications and equivalents as may be included within the scope of the invention as defined by the appended claims. Thus, the following examples which include preferred embodiments will serve to illustrate the practice of this invention, it being understood that the particulars shown are by way of example and for purposes of illustrative discussion of preferred embodiments of the present invention only and are presented in the cause of providing what is believed to be the most useful and readily understood description of formulation procedures as well as of the principles and conceptual aspects of the invention.

#### Brief Description of the Drawings

Figure 1 - illustrates the molecular structure of an exemplary transition metal substituted polyoxometalate,  $[WZnRu_2(ZnW_9O_{19})_2]^{11-}$ , active in the catalysis of molecular oxygen addition to alkenes to form epoxides.

#### Example 1

A 5 ml solution of degassed 1,2-dichloroethane containing 100  $\mu$ mol  $Q_{11}WZnRu_2(ZnW_9O_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 90 °C for nine hours in a closed vessel. The oxygen solution was cooled to room temperature and 11.2 mg cyclooctene was added.

WO 98/54165

PCT/IL98/00245

9

After 2 hours the solution was analyzed by GLC. The analysis showed a 67.5 % conversion to cyclooctene oxide.

**Example 2**

A 5 ml solution of degassed 1,2-dichloroethane containing 100  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 120 °C for six hours in a closed vessel. The oxygen solution was cooled to room temperature and 11.2 mg cyclooctene was added. After 2 hours the solution was analyzed by GLC. The analysis showed a 72.1% conversion to cyclooctene oxide.

**Example 3**

A 5 ml solution of degassed 1,2-dichloroethane containing 100  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 90 °C for nine hours in a closed vessel. The oxygen solution was cooled to room temperature and 9.4 mg norbornene was added. After 2 hours the solution was analyzed by GLC. The analysis showed a 82.1 % conversion to norbornene oxide.

**Example 4**

A 5 ml solution of degassed toluene containing 100  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 90 °C for nine hours in a closed vessel. The oxygen solution was cooled to room temperature and 11.2 mg cyclooctene was added. After 2 hours the solution was analyzed by GLC. The analysis showed a 63.7 % conversion to cyclooctene oxide.

**Example 5**

A 5 ml solution of degassed 1,2-dichloroethane containing 100  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 90 °C for nine hours in a closed vessel. The oxygen solution was cooled to room temperature and 8.4 mg 2,3-dimethyl-2-butene was

WO 98/54165

PCT/IL98/00245

10

added. After 2 hours the solution was analyzed by GLC. The analysis showed a 78.4 % conversion to 2,3-dimethyl-2-butene oxide.

**Example 6**

A 5 ml solution of degassed 1,2-dichloroethane containing 100  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 90 °C for nine hours in a closed vessel. The oxygen solution was cooled to room temperature and the solution was purged and repressurized with 1 atm propene. After 2 hours at 80 °C the solution was analyzed by GLC. The analysis showed 96% propene oxide and 4% acrolein as the only products.

**Example 7**

A 5 ml solution of degassed 1,2-dichloroethane containing 100  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 120 °C for six hours in a closed vessel. The oxygen solution was cooled to room temperature and the solution was purged and repressurized with 1 atm propene. After 2 hours at room temperature the solution was analyzed by GLC. The analysis showed 98% propene oxide and 2% acrolein as the only products.

**Example 8**

A 5 ml solution of degassed 1,2-dichloroethane containing 100  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium was kept under 1 atm molecular oxygen at 90 °C for 18 hours in a closed vessel. The oxygen solution was cooled to room temperature and 11.2 mg 1-octene was added. After 18 hours at 60 °C the solution was analyzed by GLC. The analysis showed a 76 % conversion to 1-octene oxide.

**Example 9**

A 5 ml solution of degassed toluene containing 2.5  $\mu\text{mol}$   $\text{Q}_{11}\text{WZnRu}_2(\text{ZnW}_9\text{O}_{19})_2$  in which Q is tricaprylmethyl ammonium and 280 mg was kept under 5 atm

WO 98/54165

PCT/IL98/00245

11

molecular oxygen at 90 °C for 24 hours in a closed vessel. After cooling GLC analysis showed a 15 % conversion of cyclooctene to cyclooctene oxide.

It will be evident to those skilled in the art that the invention is not limited to the details of the foregoing illustrative examples and that the present invention may be embodied in other specific forms without departing from the essential attributes thereof, and it is therefore desired that the present embodiments and examples be considered in all respects as illustrative and not restrictive, reference being made to the appended claims, rather than to the foregoing description, and all changes which come within the meaning and range of equivalency of the claims are therefore intended to be embraced therein.


PCT/IL98/00245

WO 98/54165

12

**What is Claimed is:**

1. A process for the catalytic epoxidation of alkene comprising contacting a transition metal substituted polyoxometalate and molecular oxygen with alkene.
2. A process according to claim 1 wherein said transition metal substituted polyoxometalate is first contacted with molecular oxygen followed by contact with alkene.
3. A process according to claim 1 wherein said transition metal substituted polyoxometalate is simultaneously contacted with molecular oxygen and with alkene.
4. A process according to claim 1 wherein said alkene is selected from the group consisting of branched, linear and cyclic alkenes.
5. A process according to claim 1 wherein said epoxidation is carried out at a temperature in the range of between 25 °C and 250 °C.
6. A process according to claim 1 wherein said epoxidation is carried out at super-atmospheric pressure.
7. A process according to claim 1 wherein said transition metal is a noble metal.
8. A process according to claim 1 wherein said molecular oxygen is diluted with at least inert gas.
9. A process according to claim 1 wherein said transition metal is ruthenium.



## INTERNATIONAL SEARCH REPORT

Intern. Appl. No.  
PCT/IL 98/00245A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C07D301/06 B01J31/34

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C07D B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 043 192 A (IMPERIAL CHEMICAL INDUSTRIES LIMITED) 6 January 1982 see the whole document	1
Y	DE 195 30 787 A (HOECHST AG). 27 February 1997 see the whole document	1
Y	DE 195 19 008 A (HOECHST AG) 28 November 1996 see the whole document	1
Y	DE 44 47 231 A (HOECHST AG) 4 July 1996 see the whole document	1
Y	US 5 223 631 A (CHEU P. CHENG ET AL.) 29 June 1993 see the whole document	1
-/-		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex

## \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier documents but published on or after the international filing date
- "L" documents which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

5 October 1998

Date of mailing of the international search report

12/10/1998

Name and mailing address of the ISA  
European Patent Office, P.B. 5918 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 apo nl,  
Fax (+31-70) 340-3016

Authorized officer

Kyriakakou, G

Form PCT/ISA/210 (second sheet) July 1992

page 1 of 2

## INTERNATIONAL SEARCH REPORT

Intern. Appl. Application No  
PCT/IL 98/00245

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		Relevant to claim No.
Category *	Citation of document, with indication, where appropriate, of the relevant passages	
Y	US 4 864 041 A (CRAIG L. HILL) 5 September 1989 cited in the application see the whole document	1

Form PCT/ISA210 (continuation of second sheet) (July 1992)

page 2 of 2



## INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat'l Application No  
PCT/IL 98/00245

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 43192	A	06-01-1982	AU 7188781 A JP 57045122 A US 4390738 A	07-01-1982 13-03-1982 28-06-1983
DE 19530787	A	27-02-1997	WO 9707886 A EP 0847305 A	06-03-1997 17-06-1998
DE 19519008	A	28-11-1996	WO 9637295 A	28-11-1996
DE 4447231	A	04-07-1996	CA 2208988 A WO 9620788 A	11-07-1996 11-07-1996
US 5223631	A	29-06-1993	NONE	
US 4864041	A	05-09-1989	NONE	

Form PCT/ISA/210 (patent family annex) (July 1992)